



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number : **0 598 622 A1**

(12)

EUROPEAN PATENT APPLICATION

(21) Application number : **93309210.8**

(51) Int. Cl.⁵ : **G02B 6/28**

(22) Date of filing : **18.11.93**

(30) Priority : **19.11.92 JP 310335/92**

(43) Date of publication of application :
25.05.94 Bulletin 94/21

(84) Designated Contracting States :
DE FR GB

(71) Applicant : **MITSUBISHI GAS CHEMICAL
COMPANY, INC.**
5-2, Marunouchi 2-chome
Chiyoda-Ku
Tokyo, 100 (JP)

(72) Inventor : **Arii, Mitsuzo, Mitsubishi Gas
Chemical Co.**
Inc., Tokyo Research Lab.,
1-1, Niijuku 6-chome
Katsushika-ku, Tokyo (JP)

Inventor : **Ohwada, Hisashi, Mitsubishi Gas
Chemical Co.**

Inc., Tokyo Research Lab.,
1-1, Niijuku 6-chome
Katsushika-ku, Tokyo (JP)

Inventor : **Jinnai, Kuniaki, Mitsubishi Gas
Chemical Co.**

Inc., Tokyo Research Lab.,
1-1, Niijuku 6-chome
Katsushika-ku, Tokyo (JP)

Inventor : **Kawabata, Yasunari, Mitsubishi Gas
Chemical Co.**

Inc., Tokyo Research Lab.,
1-1, Niijuku 6-chome
Katsushika-ku, Tokyo (JP)

(74) Representative : **Jenkins, Peter David et al**
PAGE WHITE & FARRER
54 Doughty Street
London WC1N 2LS (GB)

(54) **Optical device for mixing and distributing light.**

(57) The present invention is an optical device including an optical circuit in which a plurality of branched optical waveguides are connected to the light receiving side and the light ejecting side of a main optical waveguide which mixes the entering light. At least one of the branched optical waveguides has a taper construction which is wider at the joint portion to the optical fiber end than at the joint portion to the main optical waveguide, in order to improve loss variance and to reduce loss of light signals.

It is desirable that the optical circuit have the following characteristics :

$$X/Y \leq 0.8$$

$$40 \cdot Z \leq W$$

X : Width of the branched optical waveguide at the joint portion to the main optical waveguide.

Y : Width of the branched optical waveguide at the joint portion to the optical fiber.

W : Longitudinal length of the main optical waveguide (mm).

Z : Cross directional length of the main optical waveguide (mm).

It would be even more desirable that the optical circuit have the following characteristics :


$$0.4 \leq X/Y$$

$$W < 60$$

The present invention also provides a method for manufacturing the above-described optical device to be used in optical local networks and optical instrumentation control systems.

EP 0 598 622 A1

FIG.2 A



The present invention relates to an optical device and the method of manufacturing the optical device having optical waveguides which are used in, for example, local optical networks, and particularly relates to multi-mode type optical star couplers having optical waveguides (hereinafter referred to as "waveguide type multi-mode star coupler"). More particularly, the present invention relates to waveguide type multiple branched optical star couplers to be connected to graded index type multi-mode optical fibers, each fiber being 50 microns in core diameter and 125 microns in clad diameter, greatly improving the device's performance.

A multi-mode optical fiber has the advantage of high coupling efficiency with light sources, because of its large numerical aperture, compared to a single mode fiber, generally used in long distance communications. Another advantage of a multi-mode optical fiber because of its large core diameter is that the optical axes between different optical fibers or between the fiber and an optical device can be easily adjusted.

An example of a multi-mode optical fiber is a graded index type multi-mode optical fiber, 50 microns in core diameter and 125 microns in clad diameter (hereinafter referred to as the "50/125 GI optical fiber"). This type of multi-mode optical fiber is widely used, for example, in optical local networks and optical instrumentation control systems in the industrial field. It is expected that the 50/125 GI optical fibers will be further popularized and used more widely in the future because of the introduction of optical networks into offices and production sites, and because of the development of such optical networks.

An optical star coupler is an important optical device located in an optical network used to directly combine and distribute light signals. By using an optical star coupler, an optical network, the creation of an optical network used to combine and distribute light signals may be realized. Such an optical network is called a passive optical network, economically superior to an conventional active optical network, which requires the use of expensive converters to change light into electricity or electricity into light. In order to establish economically superior passive optical networks with star couplers, it is indispensable to enhance the performance of multiple branched optical star couplers, that is, multi-mode optical star couplers having many ports, frequently used in optical local networks, and to supply inexpensive products.

Manufacturing a waveguide type optical star coupler by connecting optical fibers to optical circuits (optical waveguides) for splitting and mixing light signals has two advantages: 1) multiple branched optical circuits can be easily obtained, because optical circuits are designed to have a high degree of freedom, compared to optical fiber fused type optical star couplers, which are manufactured by binding optical fibers by fusion; 2) multiple branched optical circuits are producible in large quantities.

The main performance indexes of optical star couplers are loss variance (distribution ratio) and optical loss.

Each piece of equipment or device connected to another piece of equipment or device through optical star couplers usually receives light signals at one of its receiving portions, transmitted from several other pieces of equipment or devices. Therefore, it is very important in designing the system that the receiving piece of equipment or device not be greatly affected by differences in the transmitting piece of equipment or device, and that the power of light signal received be approximately constant. In other words, light should be equally split regardless of which port the light enters the optical star coupler. If the loss variance of the optical star coupler greatly varied depending on the input ports, it would become necessary to expand the receiving sensitivity range of the receiving portion and to adjust the receiving sensitivity in accordance with the transmitter, and it would thus become difficult to design the system. As a result, the system itself would become expensive.

If the loss of the optical star coupler were small, the light receiving power of the receiving portion could be raised and the distance of the light signal transmission by optical fibers could be extended. As a result, it would become easier to design the system, and the system would be more economically efficient.

Especially, the most important issue for the future concerning the performance of multiple branched star couplers widely used in optical local networks is to improve the loss variance. The expression "multiple branched" means that the number of branches is, for example, 8 or more. An optical circuit of a waveguide type multi-mode optical star coupler is usually composed of a main optical waveguide and branched optical waveguides, which branch off respectively on the input side and on the output side of the main optical waveguide. The main optical waveguide functions to mix the mode of light signals entering the branched optical waveguides and to distribute the power of light signal to each branched optical waveguide on the output side through the main optical waveguide. Accordingly, the issue concerning the loss variance of the waveguide type multi-mode optical star coupler is to discover the optical circuit construction that enables effective mode mixing at the main optical waveguide and equal distribution of the mixed light.

A conventional method is described in, for example, Japanese Patent Laid-Open SHO No. 56-140305, which is to attain effective mode mixing through use of a waveguide type multi-mode optical star coupler. According to this method, it is suggested that the width of the main optical waveguide be made wider at the center and narrower at its both ends, that is, to construct the main optical waveguide with a taper construction in order to heighten the mixing effect in the main optical waveguide.

Conventionally, a circuit with optical waveguides, each having a constant width, i.e., diameter, from the beginning side end (a joint portion with a main optical waveguide) to the terminal side end (a joint portion with an optical fiber), has been used as the branched optical waveguide of a waveguide type multi-mode optical star coupler. However, the problem with this type of optical device is that light cannot be distributed equally from the outside ports existing along the peripheries of the central portion of the device on the light receiving side, to the outside ports on the light ejecting side.

As described above, the greatest problem of the conventional waveguide type multiple branched multi-mode optical star couplers is inconstant loss variance. Therefore, it is indispensable to make some improvements by discovering an optical circuit construction which will not cause the above described light polarization.

An aim of the present invention is to provide optical devices which can effectively mix a plurality of entering light signals and can distribute light signals equally without polarization.

Another aim of the present invention is to provide optical devices for which loss of light signals is reduced.

A further aim of the present invention is to provide passive optical networks which are highly flexible and economical.

Another aim of the present invention is to provide a method of manufacturing such optical devices.

As a result of examinations conducted in order to attain the above-mentioned aims, the inventors of the present invention have succeeded in inventing optical devices for which the loss variance is much improved over that of the conventional devices, by obtaining an optical circuit construction with slopes (tapers) which are wider at the joint portion with the optical fiber (the terminal end) than at the joint portion with the main optical waveguide (the beginning end).

In order to attain the above-mentioned aims, the present invention relates to an optical device including an optical circuit which mixes a plurality of entering light signals, distributes, and ejects the mixed light signals. This optical device includes an optical circuit in which a plurality of branched optical waveguides are connected to the light receiving side and the light ejecting side of a main optical waveguide (which mixes the entering light). Each of these branched optical waveguides has a slope which becomes wider at the terminal side end, which is to be connected to an optical fiber, than at the end of the side to be connected to the main optical waveguide.

Also, it is desirable that the above-mentioned optical circuit have the following characteristics.

$$\begin{aligned} X/Y &\leq 0.8 \\ 40 \cdot Z &\leq W \end{aligned}$$

X: Width of the branched optical waveguide at its joint portion to the main optical waveguide (the beginning end).

Y: Width of the branched optical waveguide at its end on the terminal side (the terminal end).

W: Longitudinal length of the main optical waveguide.

Z: Cross directional length of the main optical waveguide.

It would be even more desirable that the above-mentioned optical circuit also have the following characteristics:

$$\begin{aligned} 0.4 &\leq X/Y \\ W &< 60 \text{ (mm)} \end{aligned}$$

In the preferred embodiments the following features may be present.

At least one of the branched optical waveguides includes bends in order to connect to both the optical fiber and the main optical waveguide. The degree of bend becomes larger as the position of the branched optical waveguides moves toward the outside from the middle of the lateral side of the main optical waveguide. Furthermore, the bend either includes the necessary minimum number of points of inflection, or its curvature is adjusted, or both of the above are attempted so that the branched optical waveguide may be connected to the main optical waveguide as it curves.

The terminal end of the branched optical waveguide to be connected to an optical fiber is formed so as to have a width corresponding to 70 % to 100 % of the core diameter of the outside optical fiber which is connected to the terminal end.

The radius of curvature of the above-mentioned bend is set at the point from which the bend loss starts to radically increase, as can be seen in the relationship of bend loss and radius of curvature.

The above characteristics are adjusted for each branched optical waveguide in order to correct the differences in loss due to the length of the branched optical waveguide.

The branched optical waveguide includes two circular arc shaped optical transmission paths of which radii are almost the same in length, of which the centers are located in opposite positions, and which are connected to each other.

The main optical waveguide and the branched optical waveguides are formed so as to have a larger numerical aperture than those of the outside optical fibers, which are connected to the terminal ends of the

branched optical waveguides.

The optical network of this invention includes the above-mentioned optical device and optical fibers connected to the branched optical waveguides of the optical device.

The present invention includes a method of manufacturing the optical circuit, having the steps of selectively irradiating light on a base material containing light reactive monomers, and forming an optical circuit in which a plurality of branched optical waveguides are connected respectively to the light receiving side and the light ejecting side of a main optical waveguide, which mixes the incident light.

Preferably, the above-mentioned base material contains polycarbonate and the above-mentioned monomers contain at least either of the following: acrylic acid, acrylate.

In the present invention, when light with a luminous intensity of I_0 enters the optical star coupler from one port (port no. "m" on the light receiving side), and is distributed to ports on the opposite side, i.e., the light ejecting side, the total number of such ports being "n," with a luminous intensity I_n , the insertion loss ILm_n at each ejecting port is defined by the following formula (1):

$$ILm_n \text{ (dB)} = 10 \log (I_0/I_n) \quad (1)$$

Furthermore, the difference between the maximum value and the minimum value of the insertion loss ILm_n is defined as the loss variance (branching ratio) of each port when the light enters the optical device from port no. "m," and the loss variance of the entire optical star coupler having N ports on the light receiving side and N ports on the light ejecting side (hereinafter referred to as "N x N") is defined as a difference between the maximum value and the minimum value of the insertion loss of ports N x N.

The excess loss ELm of each port when the light enters the optical device from the port number "m" is defined by the following formula (2):

$$ELm \text{ (dB)} = 10 \log (I_0/\Sigma I_n) \quad (2)$$

The excess loss of the entire N x N optical star coupler is defined as the arithmetic mean of the excess loss of each port when the total number of ports is "n."

Therefore, it is necessary to reduce such losses in order to improve, i.e., to reduce, the loss variance.

Loss at the waveguide type optical star coupler will be explained hereinafter. The above-mentioned insertion loss and excess loss occur due to the loss described below.

In the process of the propagation of light within an optical waveguide, transmission loss occurs due to the absorption or scattering of light. Transmission loss is determined according to the materials or manufacturing methods of the optical waveguide, and is substantially proportional to the length of the optical waveguide. Accordingly, it is necessary to shorten the dimensions of the optical circuit as much as possible in order to reduce transmission loss.

In general, when an optical waveguide having a substantially rectangular cross section is connected to an optical fiber having a circular cross section, coupling loss (shape loss) occurs at the joint point due to the difference in the shape. In order to reduce shape loss, it is necessary to optimize the dimensions of the width of the terminal-end of the branched optical waveguide (to be connected to the optical fiber), the thickness of the optical circuit, and the core diameter of the optical fiber. As can be predicted by calculation, shape loss may be reduced to a minimum by setting the width of the terminal end, the thickness of the optical circuit, as 70 % to 100 %, or optimally about 80%, of the core diameter of the optical fiber.

Furthermore, when the optical waveguide is connected to the optical fiber, another loss occurs due to the difference in the numerical aperture between the optical waveguide and the optical fiber. The numerical aperture (NA) is represented by a core refractive index (n_{co}) and a clad refractive index (n_{cl}) as in the following formula (3).

$$NA = (n_{co}^2 - n_{cl}^2)^{1/2} \quad (3)$$

When the numerical aperture of the optical waveguide (NA_{wg}) is too small compared to the numerical aperture of the optical fiber (NA_f), a loss occurs as the light enters the optical waveguide from the optical fiber. Therefore, the optical waveguide needs to be made so as to have a larger numerical aperture than that of the optical fiber. For example, in a case of the optical waveguide formed with a base material of polycarbonate, the core refractive index (n_{co}) is 1.59, and the numerical aperture of a 50/125 GI optical fiber (NA_f) is 0.2. Thus, the optical waveguide may be manufactured to have a clad refractive index (n_{cl}^2) which will satisfy the following formula (4).

$$(1.59^2 - n_{cl}^2)^{1/2} > 0.2 \quad (4)$$

Specifically, the loss due to the difference in the numerical aperture between the optical waveguide and the optical fiber may be diminished completely if the optical waveguide is manufactured to have an $n_{cl} < 1.58$.

Furthermore, an optical waveguide which has a bend portion suffers a loss due to bend. Reduction of the loss due to bend is a very important issue for waveguide type optical star couplers, especially for multiple branched optical star couplers. The reason is that in the multiple branched optical star coupler, the degree of bend becomes larger as the position of branched optical waveguides moves toward the outside of the central

axis of the main optical waveguide.

The loss at the bend portion is explained in more detail hereinafter. When the light 10A transmitting through an optical waveguide enters the bend portion 10 from the straight portion 12, a loss, i.e., leakage of light, occurs due to the difference in guided modes (Figure 1A). Specifically, after part of the light enters the bend portion, the mode of the light increases, the light becomes a ray having a numerical aperture exceeding that of the optical waveguide, and as a result, the light leaks. Moreover, there is further loss of light 16 from leakage out of the curved optical waveguide due to irradiation, which is based on electric field distribution 18 (Figure 1B). Both the loss caused by the difference in guided modes and the loss caused by irradiation becomes greater as the curvature of the bend portion becomes larger, that is, as the bend becomes steeper.

Furthermore, although the loss due to the difference in guided modes is not affected by the central angle of the bend portion, the loss 20 increases as the direction of bend, in other words, the location of the point of inflection 22 changes (Figure 1C). On the other hand, the loss 16 due to irradiation increases in proportion to the central angle of the bend portion.

Therefore, in order to reduce the loss due to bend of the waveguide type optical star coupler, it is necessary to decrease the curvature of the bend portion of the branched optical waveguide 24, that is, to have a larger radius of curvature (shown as R_1, R_2, \dots, R_n of Figure 2B) of the waveguide type optical star coupler. However, as shown in Figure 2A, the space between the branched optical waveguides 24 at their terminal ends cannot be shorter than the clad diameter in order to be connected with optical fibers 26. Therefore, the length of the branched optical waveguides, indicated as V of Figure 2A, needs to be longer in order to enlarge the radius of curvature. In this case, as described above, the problem is that the transmission loss sometimes increases. Numeral 26A indicates a core of the optical fiber 26.

Regarding a curved optical waveguide with a constant width, the relationship between the loss due to bend (LR) and the radius of curvature (R) may be obtained by using a parameter (q) of the curved optical waveguide, applying the geometric ray tracing technique, as described in the following formulas:

$$(a) \ q \leq 1$$

$$LR = -10 \times \log (2q/3) \quad (5)$$

$$(b) \ q > 1$$

$$LR = -10 \times \log \{2/3 [1 + (q - 1)/(q + (q^2 - 1)^{1/2})]\} \quad (6)$$

The parameter (q) of the curved optical waveguide may be represented by the following formula (7) with the radius of curvature (R), width of the optical waveguide (d), core refractive index of the optical waveguide (n), and difference between the refractive indexes of the core and clad (Δn):

$$q = R \cdot \Delta n / (d \cdot n) \quad (7)$$

The radius of curvature (R) may be calculated by the following formula (8), based on the value representing the difference in positions between the beginning end and the terminal end (H) and the length (V) of the optical waveguide as shown in Figure 2B:

$$R = (H^2 + V^2) / (4 \times H) \quad (8)$$

The width of the curved optical waveguide (d), the core refractive index (n) of the optical waveguide, and the difference between the refractive indexes of the core and clad (Δn) are determined as variables independent of the radius of curvature (R) if the aforesaid shape loss and loss due to the difference in the numerical aperture are minimized. Accordingly, we may consider the relationship between the loss due to bend (LR) and the parameter (q) determined by the above formulas (5), (6), (7) and (8), as equivalent to the relationship between the loss due to bend (LR) and the radius of curvature (R).

Figure 3 illustrates the relation between the loss due to bend (LR) and the radius of curvature (R) determined by the above formulas (5), (6), (7) and (8), when the width of the optical waveguide (d) is 28 μm , the core refractive index (n) is 1.59, and the difference between the refractive indexes of the core and clad (Δn) is 0.02, that is, when the numerical aperture of the optical waveguide (NA_{wg}), as calculated by the formula (3), is 0.25. In Figure 3, the point S_0 is the boundary point of the above formulas (5) and (6).

In general, as shown on the right of point S_1 of Figure 3, there is an area in which the loss due to bend (LR) is not greatly affected by changes in the radius of curvature (R). However, setting the radius of curvature (R) as larger than is required only causes transmission loss as described above. Therefore, the radius of curvature (R) should be set within an appropriate range, considering loss due to bend (LR) and transmission loss. Specifically, there will be no problem if the radius of curvature (R) is set at the above-mentioned point S_1 , from which the loss due to bend (LR) begins to increase radically.

The optical device of the present invention may be manufactured well by using the selective photopolymerization method, as explained below.

An optical circuit is formed by selectively irradiating the light through a photomask (onto which a pattern corresponding to the optical circuit has been previously made) onto a polymer film in which light reactive monomers have been previously impregnated, thereby selectively polymerizing the monomers.

Since this selective photopolymerization method easily produces high performance optical circuits, waveguide type optical devices (multi-mode star couplers) may be manufactured at a low cost.

Moreover, by utilizing the optical circuits including optical waveguides formed by the selective photopolymerization method, high performance and inexpensive waveguide type multiple branched optical star couplers, to be used for 50/125 GI optical fibers, may be supplied to the market. Hence, constructing highly flexible and economical passive optical networks has become easier.

Embodiments of the present invention will now be described by way of example only with reference to the accompanying drawings, in which:-

Figures 1A, 1B and 1C are typical diagrams showing the occurrence of loss in a bend optical waveguide.

Figure 2A is a typical plan view of a tapered optical star circuit of the polymer waveguide type optical star coupler of the present invention.

Figure 2B is a detailed plan of a tapered branched optical waveguide.

Figure 3 is a diagram showing the relationship between loss due to bend and the radius of curvature.

Figure 4 is a perspective diagram of a typical polymer waveguide type optical star coupler of the present invention.

Figures 5A and 5B are typical diagrams showing the effects of a taper.

Figures 6A and 6B are diagrams showing the relation between the taper ratio of the branched optical waveguide, the loss variance, and excess loss.

Figures 7A and 7B are diagrams showing the relationship between the ratio of length to width of the main optical waveguide, the loss variance, and excess loss.

Figures 8A, 8B, 8C and 8D are a diagram showing the method of manufacturing the polymer optical waveguide by the selective photopolymerization method.

Figure 9 is a diagram comparing the 32 x 32 optical star coupler of the present invention and the conventional 32 x 32 optical star coupler regarding the loss variance at different ports.

As shown in Figure 4, an optical star coupler 1 is constructed by connecting an optical circuit plate 4 to optical fiber arrays 7 with an adhesive 8. This optical plate 4 is provided with a polymer film 2 on which the optical circuit is formed, and with substrates 3 which reinforce the polymer film. Each of the optical fiber arrays 7 is provided with substrates 6 and 50/125 GI optical fibers 5 which are arrayed between the substrates 6. The optical circuit of the polymer film 2 is formed by selectively polymerizing light reactive monomers which are impregnated in the transparent high polymer film.

As shown in Figures 2A and 2B, the optical circuit 30 has a main optical waveguide 32 with a uniform width, and both ends of the main optical waveguide 32 are separated into a plurality of branched optical waveguides 24. The optical circuit 30 is symmetrical at the center line L_0 , and has uniform thickness and a uniform refractive index on the whole. The branched optical waveguides 24 are arrayed in close contact with each other at their beginning ends 25 on line L_1 , connected to the main optical waveguide 32, and to optical fibers 26 at their respective terminal ends 27 on line L_2 . Moreover, all the beginning or terminal ends of the branched optical waveguides are arrayed along the straight lines L_1 or L_2 which are perpendicular to the center line L_0 . Line L_3 is the line positioned in the middle of the lines L_1 and L_2 .

The characteristic of the above-described device is that the loss variance of the multiple branched optical star coupler is greatly improved by forming the branched optical waveguides 24 in a sloped or tapered shape in order to make the width of the branched optical waveguide 24 wider at its terminal end 27 than at its beginning end 25. In particular, it is desirable that the multiple branched waveguide type optical device be constructed such that the main optical waveguide and the branched optical waveguides will satisfy the following relational expressions when the width of the beginning end of the branched optical waveguide is represented as X, the width of the terminal end of the branched optical waveguide is represented as Y, the length of the main optical waveguide is represented as W mm, and the width of the main optical waveguide is represented as Z mm. X, Y, W, and Z are indicated in Figure 2B.

$$0.4 \leq X/Y \leq 0.8 \quad (9)$$

$$40 \times Z \text{ mm} \leq W < 60 \text{ mm} \quad (10)$$

By forming the branched optical waveguide 24 in a tapered shape, the numerical aperture (NA) of the transmitted light 10A within the branched optical waveguide may increase from a small numerical aperture 32 to a large numerical aperture 34, and the angle of incidence of the light entering the main optical waveguide may be enlarged as shown in Figure 5A and 5B. In this way, the formation of the branched optical waveguide 24 in a tapered shape enables effective mixing within the main optical waveguide 32 because of the reflection of the light, and the light may be more equally distributed to the branched optical waveguides on the opposite side, i.e., the light ejecting side.

On the other hand, by making the branched optical waveguide in a tapered shape, a problem can occur in that propagation loss within the branched optical waveguide increases. Therefore, it is desirable to optimize

the ratio (X/Y) (hereinafter referred to as "taper ratio") of the width of the beginning end (X) to the width of the terminal end (Y) of the branched optical waveguide.

When the light propagates within the optical waveguide formed in a tapered shape, loss at the optical waveguide (LS) may be represented by the following formulas, based on the ray tracing method, with the numerical aperture of the optical waveguide being NA_{wg} , the numerical aperture of the incident light being NA_{in} , and the taper ratio being T.

(a) When $T \geq (NA_{in} / NA_{wg})$

$$LS = 0 \text{ dB} \quad (11)$$

(b) When $T < (NA_{in} / NA_{wg})$

$$LS = -10 \times \log \{ NA_{wg} / (NA_{in} / T) \} \text{ dB} \quad (12)$$

NA_{in} is considered to be equal to the numerical aperture of the optical fiber (NA_f) that is used. The NA_f of the 50/125 GI optical fiber is 0.2.

As described above, the optical waveguide is manufactured so as to have a numerical aperture (NA_{wg}) larger than that of the optical fiber (NA_f), $NA_{wg} > NA_f$, in order to reduce coupling loss at the joint point of the optical waveguide and the optical fiber. Namely, in the above formulas, the ratio of NA_{in} to NA_{wg} is less than 1: $(NA_{in} / NA_{wg}) < 1$, and the taper ratio is $T \leq 1$, in accordance with the definition.

There is a limit to the numerical aperture of the optical waveguides manufactured by the selective photopolymerization method due to some reason related to the manufacturing process. Therefore, when the degree of the taper becomes larger, that is, when the taper ratio becomes too small, the loss at the optical waveguide (LS) is subject to the above formula (12), and loss increases.

Accordingly, in order to reduce the loss variance without increasing excess loss of the waveguide type optical star coupler, it is desirable to set the taper ratio, i.e., the ratio (X/Y) of the beginning end width (X) to the terminal end width (Y) of the branched optical waveguide, within an appropriate range.

The inventors of the present invention conducted the following experiment with regard to 16 x 16 and 32 x 32 optical star couplers for the 50/125 GI optical fibers. Specifically, for the optical circuit of the optical star coupler, by setting the width of the terminal end of the branched optical waveguide as 40 microns, the length of the branched optical waveguide (V) as 12 mm, and the ratio (W/Z) of length (W) to width (Z) of the main optical waveguide as a constant of 40, and by changing the ratio (X/Y) of the beginning end width (X) to the terminal end width (Y) of the branched optical waveguide, the inventors were able to thoroughly examine the relation between X/Y, loss variance, and light loss (excess loss). The results are shown in Figures 6A and 6B. We can see from these results that, in either optical coupler, loss variance may be remarkably improved (reduced) by forming a taper with a taper ratio of about 20 % ($X/Y = 0.8$). When the taper ratio is 0.8 or less, loss variance was almost constant.

On the other hand, excess loss gradually increased as the taper ratio became less than 0.4. This result is due mainly to the increase of loss caused by forming the branched optical waveguide in a tapered shape. Namely, in this case, the width of the terminal end (Y) of the branched optical waveguide does not change and the shape loss indicates a constant value. Moreover, since the width of the terminal end (Y) and the ratio (W/Z) of length (W) to width (Z) of the main optical waveguide are constant, the length of the main optical waveguide (W) becomes shorter as the taper ratio becomes smaller. In this case, transmission loss of the main optical waveguide also decreases. As another cause, the radius of curvature of the branched optical waveguide increases along with the decrease of the taper ratio, and as a result, bend loss also decreases. Therefore, the increase of excess loss when the taper ratio is less than 0.4 may be caused by forming the branched optical waveguide in a tapered shape.

As described above, the lower limit of the taper ratio may be determined by controlling excess loss, and loss variance may be improved by setting the taper ratio as $X/Y \leq 0.8$. Moreover, by setting the taper ratio as $0.4 \leq X/Y \leq 0.8$ as in formula (9), loss variance may be greatly improved without increasing excess loss.

However, when the branched optical waveguide is formed in a tapered shape, it is desirable to set the length of the main optical waveguide in order to achieve effective mixing in the main optical waveguide. It is well understood that such a required length correlates with the width of the main optical waveguide.

The inventors of the present invention also conducted the following experiment concerning 16 x 16 and 32 x 32 optical star couplers for the 50/125 GI optical fibers. For the optical circuit of the optical star coupler, the length of the branched optical waveguide (V) was made constant and the taper ratio was set as 0.6. Then, the inventors thoroughly examined the relation between W/Z, the ratio of length (W) to width (Z) of the main optical waveguide, loss variance, and excess loss. The results are shown in Figure 7A and 7B. In this case, since the width of the terminal end of the branched optical waveguide (Y) is as constant as 40 microns, the taper ratio (T) and the width of the main optical waveguide (Z) (number of branches (N) x width of the beginning end (X)) are constant. Therefore, Figure 7A and 7B show the relation between the length of the main optical waveguide (W), loss variance, and excess loss.

Loss variance becomes fairly constant when W/Z is 40 or more, namely, when the length of the main optical waveguide (W) is $40 \times Z$ or more, and loss variance gradually becomes larger when W/Z is less than 40.

It is desirable for the length of the main optical waveguide (W) to be shorter in order to control and reduce excess loss. In the case of a polymer optical waveguide which is formed by the selective photopolymerization method used in the present invention, transmission loss is within the range of 0.15 dB/cm to 0.2 dB/cm. Accordingly, when the length of the main optical waveguide is 60 mm or longer, great loss occurs, if the transmission loss alone of the main optical waveguide exceeds 1 dB. According to the results of Figure 7A and 7B, excess loss may be controlled and reduced by setting the length of the main optical waveguide as shorter than 60 mm.

When the length of the main optical waveguide (W) is $40 \cdot Z$ (mm) $\leq W$, there is less loss variance, which is good. Moreover, when W satisfies the above formula (10) which is $40 \cdot Z$ (mm) $\leq W < 60$ (mm), loss variance and excess loss of the optical star coupler are both good.

As stated above, multiple branched optical star couplers superior in loss variance and excess loss may be manufactured at a high yield by setting the dimensions of the optical circuit to satisfy the above formulas (9) and (10).

As shown in Figure 1, the mode of the light increases within the tapered branched optical waveguides 3 on the light receiving side, is mixed in the main optical waveguide 2, and is distributed to the branched optical waveguides 3 on the light ejecting side. Then, opposite to the light receiving process, the mode of the light decreases in the process of light propagation through the branched optical waveguides 3 on the light ejecting side after light mixing in the main optical waveguide. Therefore, in the process of light propagation through the branched optical waveguides on the light ejecting side, no loss occurs due to the difference in the numerical aperture of the propagating light and the optical waveguides, like loss occurs in the light entering process.

As for an $N \times N$ optical star coupler, branched optical waveguides are constructed to have completely symmetrical taper ratios on the light receiving side and on the light ejecting side. In the case of an $N \times M$ star coupler, since it is usually possible to design branched optical waveguides to have almost symmetrical taper ratios on the light receiving side and on the light ejecting side, the light that finally ejects from the branched optical waveguides toward optical fibers have a numerical aperture which is not so different from that of the entering light, in other words, which is almost equal to that of optical fibers. Hence, coupling loss does not increase due to the difference in the numerical aperture of the ejecting light and the optical fibers.

As an example of the method of forming the branched optical waveguide of the present invention in a tapered shape, a circumference of each core or clad which forms a bend portion of the branched optical waveguide is made by connecting two circular arcs with identical radii, and two circumferences which form one branched optical waveguide are constructed by setting the radii of the circular arcs apart from each other. In this way, the branched optical waveguide may be easily formed in a tapered shape.

The method of forming the branched optical waveguide of the present invention in a tapered shape can be explained more specifically and in more detail by referring to Figure 2B, which illustrates the optical circuit of the present invention. The circumference of the bend portion of the branched optical waveguide may be formed by connecting two circular arcs (for example, circular arcs A_1 and B_1 , or A_2 and B_2) with the same radii (R_n), the center positions of which are opposite to each other with the circumference in between. The branched optical waveguide may be formed in a tapered shape which becomes continuously wider from the beginning end to the terminal end by designing and manufacturing the optical waveguide such that the centers of the circular arc group A (A_1, A_2, \dots, A_n) are on the straight line L_1 and the centers of the circular arc group B (B_1, B_2, \dots, B_n) are on the straight line L_2 , and by making the radii of the respective circular arcs of the circular arc groups have the relation $R_1 < R_2 < \dots < R_n$. The connecting points of the respective circular arcs, i.e., points of inflection of the circumferences, are arrayed one by one on the straight line L_3 , located in the middle of straight lines L_1 and L_2 . Therefore, as long as the number of points of inflection is kept small in number, loss due to bend, caused by increasing the mode of light, may be reduced.

The means of designing the circumferences of cores and clads of the branched optical waveguides is not limited to the above-mentioned method, as other methods or means, such as approximation by utilization of multiple dimension curves, are applicable. It is desirable to have as few points of inflection in the branched optical waveguide as possible in order to reduce loss due to bend.

The width of the beginning end (X), the width of the terminal end (Y), and the ratio of the beginning end width to the terminal end width (X/Y) of the respective branched optical waveguides may be either identical to or different from each other. The important point is to have X/Y within the range satisfying the above conditions. In the case of an optical star coupler with multiple branches, the length of the branched optical waveguides in the central part differs from those on the outer side. Therefore, even if the bias in distribution of light power in the optical device is improved, some bad loss variance is a possible result because of differences in transmission loss due to differences in the lengths of each optical waveguide. An effective means of cor-

recting the above problem is to change the ratio X/Y or the width of the terminal end Y of each of the branched optical waveguides.

The space between the terminal ends of the branched optical waveguides may be chosen within a certain range that will not worsen loss variance or excess loss. For example, as shown in Figure 2A, each space between the terminal ends of the branched optical waveguides may be the same, and may be almost equal to the outer diameter, i.e., the clad diameter, of an optical fiber, resulting in the advantage that an optical fiber array formed by previously arraying optical fibers in close contact with each other, can thus be easily connected to the optical waveguides as a lump. In this case, as the number of design parameters of the optical circuit decreases, designing the circuit becomes easier and manufacturing costs decrease.

A method of manufacturing the optical circuit used in the waveguide type optical device of the present invention is explained hereinafter, referring to Figures 8A, 8B, 8C and 8D. The first step of manufacturing the optical circuit consists of manufacturing a high transparent polymer film 81 containing a predetermined amount of light reactive monomers and sensitizers, as shown in Figure 8A; the second step consists of placing a photomask 80 over the above film, irradiating the ultraviolet light 82 on the film, and polymerizing the light reactive monomers of the portion exposed to the light, as shown in Figure 8B; the third step consists of removing the monomers 84 which did not react to the light, by applying suction drying to the film, as shown in Figure 8C; and the fourth step consists of forming clad phases 86 to protect surfaces of the optical waveguide on both the front and back surfaces of the film. An adhesive, which glues substrates in order to reinforce the optical circuit film, may also be used as the clad phases on both surfaces of the film, as shown in Figure 8D.

Figures 8C and 8D illustrate that the portion 88 exposed to the light becomes the clad phase and the portion 90 not exposed to the light becomes the core phase. However, it is possible to select a combination of matrix polymers and monomers which will make the portion exposed to the light the core phase, and the portion not exposed to the light the clad phase. Such a combination may be optionally selected according to the refractive indexes of matrix polymers and monomers.

Polycarbonate made from bisphenol is an appropriate material as a matrix polymer because it has good transparency and high mechanical strength. Since the refractive index of the matrix polymer can be as high as 1.59, acrylic acid and acrylate are preferable as light reactive monomers, because they generally have lower refractive indexes than the matrix polymer and their boiling points are comparatively low. Examples of such monomers are methyl acrylate, ethyl acrylate, acrylic acid, and trifluoroethyl acrylate.

A more detailed explanation of the present invention is made hereinafter. However, the following examples are indicated only in order to explain the present invention more specifically, and are not intended to limit the embodiments or the scope of the present invention.

EXAMPLES 1, 2 and 3

A quartz photomask, on which an optical circuit pattern was formed with the dimensions shown in Chart 1, was manufactured in order to be used for producing a 16 x 16 optical star coupler having a rectangular cross section to be connected to GI optical fibers (numerical aperture: 0.2), each of which was 50 μm in core diameter and 125 μm in clad diameter. The dimensions of the mask were designed to compensate for approximately 4 % shrinkage in the dimensions when the optical circuit is manufactured. The mask was designed to have a 125 μm space between the terminal ends of the branched optical waveguides so that the optical fibers would be arrayed in close contact with each other. A circumference of each core or clad of the branched optical waveguides was formed by connecting circular arcs with the same radii. The radius of curvature for each circumference was designed based on the relational expression $R = (H^2 + V^2) / 4H$ (the above formula (8)) (H: difference in positions between the beginning end and the terminal end of the branched optical waveguide, V: length of the branched optical waveguide).

The aforesaid selective photopolymerization method was applied to form the optical circuit. Namely, a film (thickness: 42 μm), containing polycarbonate resin synthesized from bisphenol Z (made by MITSUBISHI GAS CHEMICAL CO., INC., product name: Iupilon Z), trifluoroethyl acrylate as a monomer with a low refractive index, and benzoin ethyl ether as a sensitizer, was manufactured by a solvent casting method. After polymerizing the monomers in the portions, excluding the circuit, by exposing the film to ultraviolet rays by using the above-mentioned photomask, the monomers at the circuit portion, which did not react to the ultraviolet rays, were dried by a suction drying method, and were removed, thereby forming the optical circuit in the film. The thickness of the film after drying was 40 μm , and the numerical aperture of the optical circuit was 0.3.

The ratio of the numerical aperture of the optical fiber to those of the optical circuit was 0.67. The ratio of the thickness of the optical circuit (the longitudinal length in the directions, indicated as X-X in Figure 4) to the core diameter of the optical fiber, and the ratio of the terminal end width of the branched optical waveguide (the horizontal length in the direction indicated as Y-Y in Figure 4) to the core diameter of the optical fiber were

both 0.8.

Next, sixteen (16) strands of GI fibers, 50 μm in core diameter and 125 μm in clad diameter, from which the coating had been removed, were arrayed on a glass substrate. In this way, two optical fiber arrays were manufactured so as to array and construct the clads in close contact with each other at their ends, and the end faces of the optical fiber arrays were polished.

A 16 x 16 branched optical star coupler was manufactured by placing the above optical fiber arrays at both ends of the above optical circuit, and by gluing the optical circuit to the optical fibers while setting their optical axes at the same position.

An LED light source with a 0.85 μm wavelength (made by ANDO ELECTRIC CO., LTD., AQ-1304 type) and an optical power meter (made by ANDO ELECTRIC CO., LTD., AQ-1111 type) were used to measure the insertion loss of the optical star coupler and to calculate the loss variance and the excess loss in a conventional way, thereby obtaining the results shown as marks \circ and \square in Figure 6A, which shows the relationship between the ratio of the beginning end width to the terminal end width of the branched optical waveguide, i.e., the taper ratio, loss variance and excess loss.

EXAMPLES 4, 5, and 6

A quartz photomask, on which an optical circuit pattern was formed with the dimensions shown in Chart 1, was made in order to manufacture a 32 x 32 branched optical star coupler to be connected to GI optical fibers, each of which was 50 μm in core diameter and 125 μm in clad diameter. The spaces between the terminal ends of the branched optical waveguides were the same as in EXAMPLE 1, and the circumferences of the cores and clads of the branched optical waveguides were designed in the same manner as in EXAMPLE 1.

An optical circuit, of which the numerical aperture was 0.3 and which was 40 μm thick, was manufactured in the same manner as in EXAMPLE 1 by using the above photomask. Two optical fiber arrays, separately made by arraying thirty-two (32) optical fiber strands on glass substrates, were connected to the optical circuit in the same manner as in EXAMPLE 1 in order to manufacture a 32 x 32 optical star coupler. The insertion loss was measured, and loss variance and excess loss were calculated in the same manner as in EXAMPLE 1, thereby obtaining the results shown as marks \circ and \square in Figure 6B, which shows the relationship between the taper ratio, loss variance and excess loss.

EXAMPLES 7, 8 and 9

A quartz photomask, on which an optical circuit pattern was formed with the dimensions shown in Chart 1, was made in order to manufacture a 16 x 16 optical star coupler for GI optical fibers, each of which was 50 μm in core diameter and 125 μm in clad diameter. The spaces between the terminal ends of the branched optical waveguides were designed in the same manner as in EXAMPLE 1, and the method of forming the branched optical waveguides was the same as in EXAMPLE 1.

An optical circuit of which the numerical aperture was 0.3 and which was 40 μm thick was manufactured in the same manner as in EXAMPLE 1, and a 16 x 16 optical star coupler having the above optical circuit was manufactured. The loss variance and the excess loss were calculated from the insertion loss of the 16 x 16 branched optical star coupler, measured in the same manner as in EXAMPLE 1, thereby obtaining the results shown as marks \circ and \square in Figure 7A, which shows the relationship between the ratio of length to width of the main optical waveguide, loss variance and excess loss.

EXAMPLE 10

A quartz photomask, on which an optical circuit pattern was formed with the dimensions shown in Chart 1, was made in order to manufacture a 32 x 32 optical star coupler for GI optical fibers, each of which was 50 μm in core diameter and 125 μm in clad diameter. The spaces between the terminal ends of the branched optical waveguides were designed in the same manner as in EXAMPLE 4, and the method of forming the branched optical waveguides was the same as in EXAMPLE 4.

An optical circuit of which the numerical aperture was 0.3 and which was 40 μm thick was manufactured in the same manner as in EXAMPLE 4, and a 32 x 32 optical star coupler with the above optical circuit was manufactured. Then, the insertion loss was measured, and the loss variance and the excess loss were calculated. The results shown as marks \circ and \square in Figure 7B, show the relationship between the ratio of length to width of the main optical waveguide, loss variance and excess loss, and were obtained from EXAMPLES 5 and 10.

Chart 1

	A	B	Branched Optical Waveguide				Main Optical Waveguide		
			M	X	Y	T	W	Z	W/Z
Ex. 1	16	36	12000	17	42	0.4	11500	272	42
Ex. 2	16	41	12000	25	42	0.6	16600	400	41
Ex. 3	16	46	12000	34	42	0.8	22400	544	41
Ex. 4	32	57	17000	17	42	0.4	22300	544	41
Ex. 5	32	67	17000	25	42	0.6	33000	800	41
Ex. 6	32	79	17000	34	42	0.8	44600	1088	41
Ex. 7	16	40	12000	25	42	0.6	16000	400	40
Ex. 8	16	64	12000	25	42	0.6	40000	400	100
Ex. 9	16	76	12000	25	42	0.6	52000	400	130
Ex. 10	32	83	17000	25	42	0.6	48800	800	61

[Notes]

Ex: Example

A: Number of branches

B: Total length (mm)

M: Length of the branched optical waveguide (μm)X: Width of the beginning end of the branched optical waveguide (μm)Y: Width of the terminal end of the branched optical waveguide (μm)

T: Taper ratio

W: Length of the main optical waveguide (μm)Z: Width of the main optical waveguide (μm)EXAMPLES 11, 12, 13 and 14

A quartz photomask, on which an optical circuit pattern was formed with the dimensions shown in Chart 2, was made in order to manufacture a 16 x 16 optical star coupler for GI optical fibers, each of which was 50 μm in core diameter and 125 μm in clad diameter. The spaces between the terminal ends of the branched optical waveguides were designed in the same manner as in EXAMPLE 1, and the method of forming the branched optical waveguides was the same as in EXAMPLE 1.

An optical circuit of which the numerical aperture was 0.3 and which was 40 μm thick was manufactured in the same manner as in EXAMPLE 1, and a 16 x 16 optical star coupler with the above optical circuit was manufactured. Then, the insertion loss was measured, and the loss variance and the excess loss were calculated, thereby obtaining the results shown as marks • and ■ in Figure 6A, which shows the relationship between the taper ratio, loss variance and excess loss.

EXAMPLES 15, 16, 17 and 18

A quartz photomask, on which an optical circuit pattern was formed with the dimensions shown in Chart 2, was made in order to manufacture a 32 x 32 optical star coupler for GI optical fibers, each of which was 50 μm in core diameter and 125 μm in clad diameter. The spaces between the terminal ends of the branched optical waveguides were designed in the same manner as in EXAMPLE 4, and the method of forming the branched optical waveguides was the same as in EXAMPLE 4.

An optical circuit of which the numerical aperture was 0.3 and which was 40 μm thick was manufactured in the same manner as in EXAMPLE 4, and a 32 x 32 optical star coupler having the above optical circuit was manufactured. The insertion loss was measured, and the loss variance and the excess loss were calculated in the same manner as in EXAMPLE 4, thereby obtaining the results shown as marks • and ■ in Figure 6B, which shows the relation between the taper ratio, loss variance and excess loss.

EXAMPLES 19, 20 and 21

A quartz photomask, on which an optical circuit pattern was formed with the dimensions shown in Chart 2, was made in order to manufacture a 16 x 16 optical star coupler for GI optical fibers, each of which was 50 μm in core diameter and 125 μm in clad diameter. The spaces between the terminal ends of the branched optical waveguides were designed in the same manner as in EXAMPLE 1, and the method of forming the branched optical waveguides was the same as in EXAMPLE 1.

An optical circuit of which the numerical aperture was 0.3 and which was 40 μm thick was manufactured in the same manner as in EXAMPLE 1, and a 16 x 16 optical star coupler having the above optical circuit was manufactured. The insertion loss was measured, and the loss variance and the excess loss were calculated, thereby obtaining the results shown as marks \bullet and \blacksquare in Figure 7A, which shows the relation between the ratio of length to width of the main optical waveguide, loss variance and excess loss.

EXAMPLES 22, 23 and 24

A quartz photomask, on which an optical circuit pattern was formed with the dimensions shown in Chart 2, was made in order to manufacture a 32 x 32 optical star coupler for GI optical fibers, each of which was 50 μm in core diameter and 125 μm in clad diameter. The spaces between the terminal ends of the branched optical waveguides were designed in the same manner as in EXAMPLE 4, and the method of forming the branched optical waveguides was the same as in EXAMPLE 4.

An optical circuit of which the numerical aperture was 0.3 and which was 40 μm thick was manufactured in the same manner as in EXAMPLE 4, and a 32 x 32 optical star coupler having the above optical circuit was manufactured. The insertion loss was measured, and the loss variance and the excess loss were calculated, thereby obtaining the results shown as marks \bullet and \blacksquare in Figure 7B, which shows the relation between the ratio of length to width of the main optical waveguide, loss variance and excess loss.

COMPARATIVE EXAMPLE 1

A quartz photomask, on which an optical circuit pattern with the same width at both the beginning ends and terminal ends of the branched optical waveguides was formed with the dimensions shown in Chart 2, was made in order to manufacture a 32 x 32 optical star coupler for GI optical fibers, each of which was 50 μm in core diameter and 125 μm in clad diameter. The spaces between the terminal ends of the branched optical waveguides were designed in the same manner as in EXAMPLE 1, and the method of forming the branched optical waveguides was the same as in EXAMPLE 1.

An optical circuit of which the numerical aperture was 0.3 and which was 40 μm thick was manufactured, and a 32 x 32 optical star coupler having the above optical circuit was manufactured. The insertion loss was measured in the same manner as in EXAMPLE 5, thereby obtaining the results shown as mark \bullet in Figure 9 regarding loss variance at different ports.

Chart 2

	A	B	Branched Optical Waveguide				Main Optical Waveguide		
			M	X	Y	T	W	Z	W/Z
Ex 11	16	29	12000	8	42	0.2	5200	128	40
Ex 12	16	33	12000	13	42	0.3	8300	208	40
Ex 13	16	48	12000	38	42	0.9	24300	608	40
Ex 14	16	51	12000	42	42	1.0	26900	672	40
Ex 15	32	44	17000	8	42	0.2	10200	256	40
Ex 16	32	51	17000	13	42	0.3	16600	416	40
Ex 17	32	83	17000	38	42	0.9	48600	1216	40
Ex 18	32	88	17000	42	42	1.0	53800	1344	40
Ex 19	16	28	12000	25	42	0.6	4000	400	10
Ex 20	16	36	12000	25	42	0.6	12000	400	30
Ex 21	16	86	12000	25	42	0.6	62000	400	155
Ex 22	32	42	17000	25	42	0.6	8000	800	10
Ex 23	32	58	17000	25	42	0.6	24000	800	30
Ex 24	32	97	17000	25	42	0.6	62400	800	78
CE 1	32	55	17000	42	42	1.0	20600	1344	15

[Notes]

Ex: Example

CE: Comparative Example

A: Number of branches

B: Total length (mm)

M: Length of the branched optical waveguide (μm)X: Width of the beginning end of the branched optical waveguide (μm)Y: Width of the terminal end of the branched optical waveguide (μm)

T: Taper ratio

W: Length of the main optical waveguide (μm)Z: Width of the main optical waveguide (μm)

In the 32 x 32 branched optical star coupler constructed with a conventional optical circuit connected to 50/125 GI optical fibers, as the entering light enters from the ports and propagates toward the outside ports, polarization of light occurs and the distribution of light worsens. More particularly, in Figure 8, when comparing the light entering the ports in the center portion, for example, ports nos. 12 to 20, with the light entering the ports in the outermost positions, nos. 1 and 32, there is a substantial difference in the loss variance, measured at 18 dB. The reason for this difference is that the light entering the outside ports is extremely likely to be distributed to the opposite outside ports and the adjacent ports on the light ejecting side.

On the contrary, in the optical star coupler corresponding to the one indicated as \circ in Figure 9, the loss variance is substantially constant from outside ports to the center portion, and the light entering the main optical waveguide from outside ports is equally distributed to the ports on the light ejecting side.

In the present invention, an optical device with optical waveguides, i.e., a multiple branched multi-mode type optical star coupler, with good loss variance or not only with good loss variance but also little excess loss, can be produced. Moreover, it is possible to manufacture and supply such optical circuits at high yield. Implementation of the present invention makes the supply of high performance, inexpensive waveguide type multi-mode multiple branched optical star couplers to the market possible, enhancing the reliability of multi-mode optical networks (LAN), and makes construction of inexpensive systems with the intention of wide distribution possible.

Claims

1. An optical device having an optical transmission means which mixes a plurality of entering light signals, and then distributes and ejects the mixed light signals; said optical transmission means comprising:
an optical circuit in which a plurality of branched optical waveguides are connected to the light receiving side and the light ejecting side of a main optical waveguide, which mixes the entering light; and
wherein at least one of said branched optical waveguides having a slope of which the width is wider at its end on the terminal side than at its end on the side to be connected to the main optical waveguide.
2. An optical device according to Claim 1, wherein said optical circuit has the following characteristics:

$$X/Y \leq 0.8$$

$$40 \cdot Z \leq W$$

X: Width of said branched optical waveguide at its joint portion with said main optical waveguide.
Y: Width of said branched optical waveguide at its end on the terminal side.
W: Longitudinal length of the main optical waveguide (mm).
Z: Cross directional length of the main optical waveguide (mm).
3. An optical device according to Claim 2, wherein said optical circuit has the following further characteristics:

$$0.4 \leq X/Y$$

$$W < 60$$
4. An optical device according to Claim 1, wherein at least one of said branched optical waveguides comprises bend with points of inflection.
5. An optical device according to Claim 1, wherein the terminal end of said branched optical waveguide has a width corresponding to 70 % to 100 % of the core diameter of an optical fiber, to be connected to said terminal end.
6. An optical device according to Claim 4, wherein the radius of curvature of said bend is set at the point from which the bend loss begins to increase radically, as may be seen in the characteristics of bend loss and radius of curvature.
7. An optical device according to Claim 3, wherein said characteristics are adjusted for each branched optical waveguide in order to correct the differences in loss due to the different lengths of said branched optical waveguides.
8. An optical device according to Claim 4, wherein the branched optical waveguide comprises two circular arc shaped optical transmission paths of which the radii are almost the same in length, the centers of which are located in opposite positions, and which are connected to each other.
9. An optical device according to Claim 1, wherein said main optical waveguide and said branched optical waveguides have larger numerical aperture than those of the outside optical fibers to be connected to the terminal ends of the branched optical waveguides.
10. An optical device according to Claim 1, further comprising an optical fiber to be connected to the branched waveguides.
11. An optical network, comprising:
an optical device which mixes a plurality of entering light signals and then distributes and ejects the mixed light signals, said optical device having an optical circuit in which a plurality of branched optical waveguides are connected to the light receiving side and the light ejecting side of a main optical waveguide, which mixes the entering light; and
optical fibers connected to said branched optical waveguides;
wherein at least one of said branched optical waveguides has a slope of which the width is wider at its end on the terminal side than at its end on the side to be connected to said main optical waveguide.
12. An optical network according to Claim 11, wherein said optical circuit has the following characteristics:

$$X/Y \leq 0.8$$

$$40 \cdot Z \leq W$$

- X: Width of said branched optical waveguide at its joint portion to the main optical waveguide.
 Y: Width of said branched optical waveguide at its end on the terminal side.
 W: Longitudinal length of the main optical waveguide (mm).
 Z: Cross directional length of the main optical waveguide (mm).

13. An optical network according to Claim 11, wherein said optical circuit has the following characteristics:

$$0.4 \leq X/Y$$

$$W < 60$$

14. An optical network according to Claim 11, wherein said optical fiber comprises a graded multi-mode type optical fiber.

15. An optical network according to Claim 14, wherein said graded multi-mode type optical fiber is 50 microns in core diameter and 125 microns in clad diameter.

16. An optical network according to Claim 11, wherein the terminal end of said branched optical waveguide has a width corresponding to 70 % to 100 % of the core diameter of an optical fiber, to be connected to said terminal end.

17. An optical network according to Claim 11, wherein at least one of said branched optical waveguides comprises bend with points of inflection.

18. An optical network according to Claim 17, wherein the radius of curvature of said bend is settled at the point from which the bend loss begins to increase radically, as may be seen in the characteristics of bend loss and radius of curvature.

19. An optical network according to Claim 13, wherein said characteristics are adjusted for each branched optical waveguide in order to correct the differences in loss due to the different lengths of said branched optical waveguides.

20. An optical network according to Claim 11, wherein said main optical waveguide and said branched optical waveguides have larger numerical aperture than those of the optical fibers to be connected to the terminal ends of the branched optical waveguides.

21. An optical network according to Claim 17, wherein said branched optical waveguide comprises two circular arc shaped optical transmission paths of which the radii are almost the same in length, the centers of which are located in opposite positions, and which are connected to each other.

22. A method of manufacturing an optical circuit, comprising the steps of:

selectively irradiating the light on a base material containing light reactive monomers; and
 forming an optical circuit in which a plurality of branched optical waveguides are connected respectively to the light receiving side and the light ejecting side of a main optical waveguide, which mixes the entering light,

wherein at least one of said branched optical waveguides is formed to have a slope of which the width becomes wider at its end on the terminal side than at its end on the side to be connected to the main optical waveguide.

23. A method of manufacturing the optical circuit according to Claim 22, wherein said optical circuit is constructed so as to have the following characteristics:

$$X/Y \leq 0.8$$

$$40 \cdot Z \leq W$$

- X: Width of said branched optical waveguide at its joint portion to the main optical waveguide.
 Y: Width of said branched optical waveguide at its end on the terminal side.
 W: Longitudinal length of the main optical waveguide.
 Z: Cross directional length of the main optical waveguide.

24. A method of manufacturing the optical circuit according to Claim 22, wherein said optical circuit is constructed to have the following further characteristics:

$$0.4 \leq X/Y$$

W < 60 (mm)

25. An optical circuit according to Claim 22, wherein said base material contains polycarbonate, and said monomers contain at least one of acrylic acid and acrylate.

5

10

15

20

25

30

35

40

45

50

55

FIG.1 A




FIG.1 B




FIG.1 C




FIG. 2 A




FIG. 2B




FIG.3




FIG.4




FIG.5A




FIG.5B




FIG.6A




FIG.6B




FIG.7A




FIG.7B




FIG.8A




FIG.8B




FIG.8C




FIG.8D





FIG.9





European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 93 30 9210

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.5)
X	JOURNAL OF LIGHTWAVE TECHNOLOGY. vol. LT-3, no. 3, June 1985, NEW YORK US pages 556 - 559 S. OHSHIMA ET AL. 'Small Loss-Deviation Tapered Fiber Star Coupler for LAN'	1	G02B6/28
Y	* the whole article *	5,10,11, 22,25	
Y	---		
Y	PATENT ABSTRACTS OF JAPAN vol. 9, no. 137 (P-363)(1860) 12 June 1985 & JP-A-60 017 706 (NIPPON DENKI K.K.)	10,11	
A	* abstract *	4,17	
Y	---		
Y	EP-A-0 428 951 (MITSUBISHI GAS CHEMICAL COMPANY)	5,22,25	
A	* abstract *	14,16	
	* page 6, line 29 - page 7, line 8 *		
	* figure 8 *		
A	---		
A	APPLIED OPTICS. vol. 27, no. 15, 1 August 1988, NEW YORK US pages 3177 - 3179 I. KATO ET AL. 'New fabrication method of a star coupler by stacking polymer films' * the whole article *	2,12,23	TECHNICAL FIELDS SEARCHED (Int.Cl.5) G02B
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 20 January 1994	Examiner Luck, W
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons</p> <p>Δ : member of the same patent family, corresponding document</p>			

EPO FORM 1503 (12/92) (P/C01)